



Industrial Marine Architectural Coatings

TECHNICAL DATA SHEET

CODE : 29006

YACHT ENAMEL

DESCRIPTION

One component high gloss alkyd enamel with fast drying for the protection of interior and exterior areas.

RECOMMENDED USE

For metallic and wooden surfaces like metallic constructions, boat, industrial equipment etc.

PHYSICAL DATA

- **Shade:** Various RAL shades such as and shades after special order.
- **Finish:** High gloss
- **Volume solids:** 48 % \pm 2
- **Specific gravity:** 1 – 1,05 Kg / Lt
- **Indicated dry film thickness:** Dry film 30 – 40 μ m
- **Theoretical spreading rate:** 10 – 12 m²/Lt
- **Drying time:**
 - **Dry to touch:** 2 hours 23° C 50 % Relative humidity
 - **Final:** 4 - 6 hours 23° C 50 % Relative humidity

SURFACE PREPARATION

All the surfaces must be dry and clean before application of the paint. We recommend antirust primer for metallic surfaces.

APPLICATION DETAILS

- Stir the paint well before its use. The product is applied by spray gun, airless and by brush on smaller surfaces.
- Dilution: 10 – 20 % with solvent N' 404 or N' 402 or N'601.
- Tools cleaning: with solvent N'404 or N' 402 or N'601.

SAFETY

Use the product to well ventilated place.
Wear suitable protective gloves, eyeglasses and face protection.

The above information and our technical advice-whether verbal or in writing-are given in good faith and according to our tests. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses.

ED 12/ 19

Technical Data Sheet

HYDROTON SA PAINTS & VARNISHES INDUSTRY

16^okm New National Road Thessaloniki – Kilkis P.O. 572 00 THESSALONIKI GREECE
Tel : 0030 23940 31-465, 0030 23940 32-019 <http://www.hydroton.gr> e-mail:hydroton@hydroton.gr

FOR PROFESSIONAL USE ONLY